

FOR PROFESSIONAL USE ONLY**SPEC DATA SHEET**

InStrip is a paste-type, multi-layer, interior and exterior paint stripper that can lift primers, solvent, and water based paints. InStrip also removes various wood finishes, such as varnish, shellac, and stains. InStrip has a pleasant odor and is non-hazardous, which makes in ideal for interior paint stripping.

ADVANTAGES

- Non-toxic and non-corrosive
- Low VOC
- Pleasant odor
- Will not fuzz or discolor hard or soft wood
- Suitable for furniture stripping
- Paste clings to vertical surfaces
- Has a wide range of applications
- pH Neutral
- Safer for the applicator

LIMITATIONS

- Do not get on surfaces not intended to be stripped.

**For information about soft metals, please see our soft metal Issue Statement at our website for more complete guidance.*

TECHNICAL DATA

| | |
|-----------------------------|---------------|
| Appearance: | Beige paste |
| Odor: | Pleasant odor |
| Physical State: | Paste |
| pH: | 7.5 |
| Boiling Point: | N/A |
| Specific Gravity (water=1): | 1.03 @ 77° F |
| Evaporation Rate: | N/D |
| Solubility in Water: | Negligible |
| Flash Point: | N/D |
| Viscosity | N/A |
| Decomposition Temp: | N/D |
| Oxidizing Properties: | N/D |

PREPARATION

Protect adjacent surfaces and surrounding building hardware not intended to be stripped. Avoid direct contact with foliage. Cover landscape using polyethylene or other proven protective material to capture the paint being removed.

SURFACE & AIR TEMPERATURES

Excessively high or low temperatures will produce poor results and possible harm. Best cleaning results are obtained when air and surface temperatures are above 40° Fahrenheit or less than 90° Fahrenheit. Do not clean when temperatures are below freezing or will be overnight. If freezing conditions exist, allow adequate time for the surface to thaw. If air temperatures exceed 90° Fahrenheit, flash cool the surface with water before applying product. Do not allow products to dry on the surface. Always rinse thoroughly while still wet.

PRE-TESTING

Always test prior to beginning full-scale cleaning operations. Pre-testing will determine suitability and effectiveness on each type of surface and coating. Pre-testing will also determine dwell times and number of applications required to achieve desired results. Pre-testing will show any potential or adverse reactions to adjacent surfaces. Allow test areas to thoroughly dry before evaluating final appearance and results.

SAFETY INFORMATION

Always wear goggles and chemical resistant gloves when handling this product. Read the Safety Data Sheet for additional safety and health hazard information prior to use. Do not get in eyes, on skin, or on clothing. Do not wear contact lenses when using this product. If material comes in contact with clothing, wash before re-use. Do not dilute this product with any other product except clean water. Do not use any other application other than specified in the application instructions. Keep container closed when not in use. Use with adequate ventilation. Use NIOSH/MSHA approved respiration devices when adequate ventilation is not available. Though the potential for fuming is minimal, take precautions to avoid exposing building occupants to fumes. Do not remove the label from the container. Dispose of empty containers in accordance with federal, state, and local requirements.

CAUTION: KEEP AWAY FROM CHILDREN

**CHEMTEL 24 HOUR EMERGENCY RESPONSE
SERVICE NUMBER - 1-800-255-3294**

THE WAY OF THE FUTURE



FOR PROFESSIONAL USE ONLY

SPEC DATA SHEET

DILUTIONS

InStrip is always used undiluted (straight)

COVERAGE RATES

Coverage rates with InStrip will vary from 25-100 sq. ft. per gallon depending on the thickness of application.

APPLICATION INSTRUCTIONS

1. Apply InStrip with a brush or a roller to a dry surface.
2. Allow the proper dwell time determined by pre-testing.
3. Wipe off, scrape off, or rinse off using high pressure. Do not use pressure that marks the surface.

Note: textured surfaces may require a second coat of InStrip. Pre -testing will determine this.

RINSING

Rinse all residue from the surface. When in doubt, follow the manufacturers recommended P.S.I. for the substrates. **Do not use a zero-degree nozzle.**

SPILL OR LEAK PROCEDURES

Check with state, local, or federal regulation for waste disposal methods in the area. Wear proper protective equipment while doing clean-up. For large spills, dike and contain for intended use. For residual, use a chemical absorbent material. For small spills, use a chemical absorbent material and place in an approved container for disposal.

CONTAINER HANDLING/STORAGE

Store product in a cool, dry place away from alkali-based materials. Vent the bung cap before opening. Keep container tightly closed when not in use. Wash thoroughly after handling. Do not use container as a dilution or rinsing vessel. Do not cut, grind, or weld on or near container. Empty containers retain residue and must be handled as if full.

INSTRUCTIONS IN CASE OF CONTACT OR EXPOSURE

Eyes: Flood with water for 15 minutes. If irritation develops, seek medical attention.

Skin: Wash off with soap and water. Follow with a good emollient. If irritation develops, seek medical attention.

Ingestion: Drink lots of water to dilute. Do not induce vomiting. Seek immediate medical attention.

Inhalation: Move to fresh air. If irritation develops, seek medical attention.

NOTICE

This product has been classified in accordance with the hazard criteria of the CFR.

DISCLAIMER

The information herein is given in good faith, but no warranty, either expressed or implied is made. Final determination of the suitability of any material is the sole responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot be sure or guarantee these are the only hazards which exist.

CUSTOMER SERVICE

Factory personnel are available for assistance Monday through Friday from 8am to 5pm EST at (724) 656-1055. Questions can also be sent to info@eacochem.com. A reply can be expected by the following business day.